TO THE

INVESTOR IN PEOPLE

The Patent Office

Concept House

Cardiff Road RECEIVED
Newport 1 C IAN 200

South Wales

1 6 JAN 2004

NP10 80001PO

PCT



I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Dated

4 December 2003

BEST AVAILABLE COPY



Petents Act 1977 (Rufe 16)



Request for grant of a p (See the notes on the back of this form

an explanatory leaflet from the Passat Office to bely you fill in this form)

The Patent Office

Cardiff Road Newport Gwent NP9 IRH

۱.	Your reference	SMC 60558/GB/P1	
	5 5 MAY 2002		18NOVO2 E763924-1 D02944
2,	Patent application trumber 1 5 WW 2002 (The Patent Office will fill in this pant)	226710.2	P01/7700 0.00-0226710.2
3.	each applicant (underline all curnams)	Avecia Limited Hexagon House Blackley Manchester, M9 8Zt United Kingdom	s .
	Patents ADP number (17 you troop 10)	07764137001 ~	•
	If the applicant is a corporate body, give the country/state of its incorporation	GB	is .
I.	Tide of the invention	INKS	
i,	Name of your agent (If you have one)	MAYALL, John	A LONG THE PARTY OF THE PARTY O
•	"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	Avecia Limited Hexagon House Blackley Manchester, M9 82 United Kingdom	'S
	Patents ADP number (If you know it)	6244313002	624431300L
5.	If you are declaring priority from one or more earlier parent applications, give the country and the date of filing of the or of each of these	Country Priority appli	inition number Date of filing (day / month / year)
	carlier application number		
7.	If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of eadler application	Date of illing (day / month / year)
8.	is a statement of inventorship and of right to grant of a parent required in support of this request? (Answer Ver' if: a) any applicant named in part 3 is not an inventor, or b) there is an inventor who is not maned as an applicant, or a) any named applicant is a corporate body.		

Patents Form 1/77

0052797 15-Nov-02 0 Form 1/77

Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description

09

Ciaim(s) Abstract

Drawing(s)

). If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patroit (Putmer Form 7/77)

Request for preliminary examination and starch (Patents Form 9/77)

Request for substantive examination (Patents Form 10/77)

> Any other documents (please specify)

I/We request the grant of a parent on the basis of this application.

Signature

Danie 15 11102

Avecla Limited Authorised Signatory

2: Name and daytime telephone number of person to contact in the United Kingdom Mrs K.M. Pinder/Miss G. Terry 0161 721 1361/2

fter an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication r communication of the invention should be probibited or restricted under Section 22 of the Patents Act 1977. You All be informed if it is necessary to probibit or restrict your invention in this way. Furthermore, if you live in the witted Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting ortisen permission from the Patent Office unless an application has been filed at least 6 weeks beforeband in the inited Kingdom for a patent for the same invention and either no direction prohibiting publication or communication bis been given, or any such direction bis been revoked.

- a) If you need bely to fill in this form or you bave any questions, please contact the Patent Office on 0645 500505.
- Write your enswers in capital letters using black into or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please constitute on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Rorm 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and dute it.
- For details of the fee and ways to pay please contact the Fatent Office.

Patents Form 1/7



<u>APPLICANTS</u> AVECIA LIMITED

TITLE

INKS ·



10

15

20

25

30

35

<u>INKS</u>

This Invention relates to inks of use in ink let printing ("IJP"). IJP is a non-impact printing technique in which droplets of ink are ejected through a fine nozzle onto a substrate without bringing the nozzle into contact with the substrate.

There are many demanding performance requirements for inks used in LIP. For example they desirably provide sharp, non-feathered images having good water-fastness, light-fastness and optical density. The inks are often required to dry quickly when applied to a substrate to prevent smudging, but they should not form a crust over the tip of ink jet nozzles because this will stop the printer from working. The inks should also be stable to storage over time without decomposing or forming a precipitate which could block the fine nozzles.

We have now devised an ink which is particularly useful for ink jet printing.

According to the present invention there is provided an ink comprising a liquid medium and a tris-azo compound of Formula (1) or salt thereof:

Formula (1)

wherein the liquid medium comprises water and an organic solvent.

When compound of Formula (1) is in the form of a salt preferred salts are alkall metal salts, especially lithium, sodium and potassium salts, ammonium and substituted ammonium salts. Especially preferred salts are salts with ammonia and volatile amines. The free acid form may be converted into a salt using known techniques. For example, an alkali metal salt may be converted into a salt with ammonia or an amine by dissolving an alkali metal salt of the composition in water, acidifying with a mineral acid and adjusting the pH of the solution to pH 9 to 9.5 with ammonia or the amine and removing the alkali metal cations by dialysis.

The ink preferably comprises:

- (a) from 0.01 to 30 parts of a compound of Formula (1) or salt thereof; and
- (b) from 70 to 99.99 parts of a liquid medium comprising water and an organic solvent;

wherein all parts are by weight and the number of parts of (a)+(b)=100.

The number of parts of component (a) is preferably from 0.1 to 20, more preferably from 0.5 to 15, and especially from 1 to 5 parts. The number of parts of component (b) is preferably from 99.9 to 80, more preferably from 99.5 to 85, especially from 99 to 95 parts.

COCT TITOTO

בונים המשב במשם בינים בונים בינים בי

i



10

٠٠;.٠

٠.

: ;

15

20

٠.,٠

٠. :

Ι.

25

ď

30

٧,

ٺ

₂, 35

40

٠:

Preferably component (a) is completely dissolved in component (b). Preferably component (a) has a solubility in component (b) at 20°C of at least 10%. This allows the preparation of liquid dye concentrates which may be used to prepare inks and reduces the charice of the dye precipitating if evaporation of the liquid medium occurs during storage.


The weight ratio of water to organic solvent is preferably from 99:1 to 1:99, more preferably from 99:1 to 50:50 and especially from 95:6 to 80:20.

It is preferred that the organic solvent present in the mixture of water and organic solvent is a water-miscible organic solvent or a mixture of such solvents. Preferred watermiscible organic solvents include C1-a-alkanols, preferably methanol, ethanol, n-propanol, isopropanol, n-butanol, sec-butanol, tert-butanol, n-pentanol, cyclopentanol and cyclohexanol; linear amides, preferably dimethylformamide or dimethylacetamide; ketones and ketone-alcohols, preferably acetone, methyl ether ketone, cyclohexanone and diacetone alcohol; water-miscible ethers, preferably tetrahydrofuran and dioxane; diols, preferably diols having from 2 to 12 carbon atoms, for example pentane-1,5-diol, ethylene. glycol, propylene glycol, butylene glycol, pentylene glycol, hexylene glycol and thiodiglycol poly-alkyleneglycols, preferably diethylene glycol, triethylene glycol, and oligo- and polyethylene glycol and polypropylene glycol; triols, preferably glycerol and 1,2,6-hexanetrici; mono-C14-alkyl ethers of diols, preferably mono-C14-alkyl ethers of diols having 2 to 12 carbon atoms, especially 2-methoxyethanol, 2-(2-methoxyethoxy)ethanol, 2-(2-ethoxyethoxy)-ethanol, 2-[2-(2-methoxyethoxy)ethoxy]ethanol, 2-[2-(2-ethoxyethoxy)ethoxy]-ethanol and ethylenegiycol monoallylether, cyclic amides, preferably 2-pyrrolidone, N-methyl-2-pyrrolidone, N-ethyl-2-pyrrolidone, caprolactam and 1,3-dimethylimidazolidone; cyclic esters, preferably caprolactone; sulphoxides, preferably dimethyl sulphoxide and sulpholane. Preferably the liquid medium comprises water and 2 or more, especially from 2 to 8, water-soluble organic solvents.

Typically the liquid medium will further comprise one or more surfactants, for example anionic and/or nonionic surfactants. Examples of anionic surfactants include: Sulfonate surfactants such as Sulfosuccinates (AerosolTM OT, A196; AY and GP, available from CYTEC) and Sulfonates (AerosolTM DPOS-45, OS available from CYTEC; WitconateTM C-50H available from WITCO; DowfaxTM 8390 available from DOW); and Fluoro surfactants (FluoradTM FC99C available from 3M). Examples of nonionic surfactants include: Fluoro surfactants (FluoradTM FC170C available from 3M); Alkoxylate surfactants (TergitolTM series 15S-5, 15S-7, and 15S-9 available from Union Carbide); and Organdsilicone surfactants (SilwetTM L-77 and L-76-9 available from WITCO).

One or more buffers may optionally be included in the liquid medium to modulate pH of the ink. The buffers can be organic-based biological buffers or inorganic buffers, preferably, organic-based. Examples of preferably-employed buffers include tris(hydroxymethyl)aminomethane (TRIS), available from companies such as Aldrich Chemical (Milwaukee, Wis.), 4-morpholineethanesulfonic acid (MES), 4-morpholinepropanesulfonic acid (MOPS), and beta-hydroxy-4-morpholinepropanesulfonic

Ę,



15

20

25

30

35

acid (MOPSO). Further, the buffers employed should provide a pH ranging from about 3 to about 9 in the practice of the invention, preferably about 4 to about 6 and most preferably from about 4 to about 5.

One or more of the blocides commonly employed in inkjet inks may optionally be included in the Ilquid medium, such as NuoseptTM 95, available from Huls America (Piscataway, N.J.); ProxelTM GXL, available from Zeneca (Wilmington, Del.); and glutaraldehyde, available from Union Carbide Company (Bound Brook, N.J.) under the trade designation Ucarcide 250.

The ilquid medium may optionally also include one or more metal chelator. Such chelators are used to bind transition metal cations that may be present in the ink. Examples of preferred metal chelators include: ethylenediaminetetraacetic acid ("EDTA"), diethylenediaminepentaacetic acid ("DPTA"), trans-1,2-diaminocyclohexanetetraacetic acid ("CDTA"), ethylenedinitrilotetraacetic acid ("EGTA"), or other chelators.

In one embodiment links according to the invention have a pH of from about 3 to about 5, preferably from about 3.5 to about 4.5. In another embodiment the pH of the link is preferably from 4 to 11, more preferably from 7 to 10.

The viscosity of the ink at 25°C is preferably less than 50cP, more preferably less than 20 cP and especially less than 5cP.

The ink may also contain additional components conventionally used in ink jet printing inks, for example viscosity and surface tension modifiers, corrosion inhibitors and kogation reducing additives.

For the avoidance of doubt, the present invention relates solely to links containing the compound of Formula (1). The scope of protection sought in this patent specification does not include the compound of Formula (1) per se (i.e. when it is not in an ink).

The links of the present invention provide prints of attractive, neutral black shades that are particularly well suited for the link jet printing of text and images. The links have good storage stability and low tendency to block the very fine nozzles used in link jet printers. Furthermore, the resultant images have good optical density, light-fastness, wet-fastness and resistance to fading in the presence of oxidising air pollutants (e.g. ozone). The links maybe incorporated into link jet cartridges and used in link jet printers by any of the numerous known methods, for example as described in the many patent applications by Hewlett Packard, Seiko Epson, Canon and Lexmark. For example, the links may be injected into an empty link jet cartridge and the cartridge re-used in an link jet printer in the conventional manner.

The invention is further illustrated by the following Example in which all parts and percentages are by weight unless specified otherwise. The abbreviation "Ac" means CH_3CO -.

10

15

20

25

30

Example.1

Preparation of an ink comprising:

Preparation of intermediate 2,5-di-(2-acetoxyethoxy)aniline

Step 1 - Preparation of 1.4-bis-(2-acetoxyethoxy)hydrogulnone

Hydroquinonebis-(2-hydroxyethyt)ether (179g), acetic acid (100ml) and acetic anhydrida (300ml) were stirred and heated under reflux overnight. After cooling to room temperature and drawning into water (21) the product was isolated by filtration, washed with water, dried and recrystallised from ethanol to give 212g of product.

Step 2 - Preparation of 2-Nitro-1,4-bis-(2-acetoxyethoxy)hydroquinone

The product of step 1 (211.5g) was dissolved in acetic acid (1800ml). A mixture of nitric acid (51,9ml) and acetic acid (200ml) was then added over 20 minutes keeping the temperature below 20°C. After stirring at room temperature overnight the solution was drowned into water (9) and the product isolated by filtration, washed with water and recrystallised from ethanol to give 209g of product.

Step 3 - Preparation of 2,5-di-(2-acetoxyethoxy)antline

2-Nitro-1,4-bis-(2-acetoxyethoxy)hydroquinone (115g) was dissolved in ethanol at 50°C and reduced with hydrogen in the presence of palladium catalyst (2g, 5%Pd/C). When uptake of hydrogen ceased the solution was screened to remove the catalyst and the filtrates allowed to cool to room temperature. The crystalline solld was isolated by filtration and dried under vacuum to give 90g of product.

Stage one - Preparation of monoazo-4-(4-Acetylamino-2-sulpho-3-phenylazo)-2,5-di-(2acetoxyethoxy)anlline



10

15

20

30

35

4-Amino-3-sulphoacetanilide (174g; 0.6 mot) was stirred in water (2.5l) at pH 9 and sodium nitrite (45.64g; 0.66 mol) added. The solution was added to ice/water containing concentrated hydrochloric acid (180ml) with stirring. After stirring for 1.5h at less than 10°C the excess nitrous acid was destroyed by the addition of sulphamic acid. 2,5-di-(2-acetoxyethoxy)aniline (178.2g; 0.6mol) was dissolved in acetone (1900 ml) and added to the above diazonium salt suspension at 0-10°C followed by the slow addition of pyridine (30ml). After stirring overnight at room temperature the precipitated product was filtered-off, washed with water. The damp paste was then stirred in acetone, filtered and dried (50°C) to give a an orange solid (210g; 64%).

Stage two - Preparation of bisazo intermediate

The monoazo product from Stage one (24.75g; 0.05mol) was dissolved in water (300ml) with stirring at pH 10 to which sodium nitrite (6.90g; 0.1mol) and acetone (200ml) were added. The resulting mixture was then added to 0.10M hydrochloric acid (70ml) with stirring at room temperature. After stirring for 1h, the excess nitrous acid was destroyed by the addition of sulphamic acid. The resulting diazonium salt was then added to a stirred solution of chromotropic acid (20.00g; 0.05mol) at less than 10°C at pH 7-8 maintained by the addition of 2N lithium hydroxide when necessary. After stirring overnight the product was precipitated by the addition of 26% (w/v) lithium chloride then filtered and washed with 30% lithium chloride solution. The resulting damp paste was suspended in water (700ml) and lithium hydroxide hydrate (26.00g; 0.60mol) added and the solution fieated at 70°C. After 3h the solution neutralised to pH 6 – 7 by the addition of concentrated hydrochloric acid. The product was precipitated by the slow addition of 20 % lithium chloride, filtered and washed with 25% (w/v) lithium chloride solution. The damp paste was dissolved in water and then dialysed to low conductivity. The solution was evaporated to dryness (70 °C) to give a black powder (25.5g; 67%)

Stage Three- preparation of title dye

The amino disazo compound from Stage Two (0.016 mol) in water (160ml) was stirred at pH 9 to which calcolene oil (1ml) and sodium nitrite (1.20g; 0.0174 mol) were added. The resulting solution was stirred then added to ice / water (100g) containing concentrated hydrochloric acid (5ml) with stirring at 0 - 10°C. After stirring for 1h at 0 - 10°C the excess nitrous acid was destroyed by the addition of sulphamic acid. The resulting



20 .

diazonium salt was added to a stirred solution of 1-ethyl-1,2-dihydro-6-hydroxy-4-methyl-2-oxo-3-pyridinecarbonitrile (3.10g, 0.158 mol) in water (100ml) at 0~10°C and then adjusted to pH 7. After stirring overnight the solution was poured into acetone (3l) with stirring, filtered and washed with acetone. The solid dissolved in water and dialysed to low conductivity to give after evaporation (80°C) a black powder (8.9g; 61%; ϵ_{max} 81,232 and a λ_{max} 601nm.

Stage 4 - Preparation of Ink

10 An ink may be prepared having the following formulation:

2-Pyrrolidone 5 parts

Thiodigiyool 6 parts

Surfynol[™] 465 1 part (from Air Products Inc., USA)

Dye

3 parts

Water

86 parts

Example 2 - Ink Formulations

lnks may be prepared according to the following formulation wherein Dye is the compound from Example 1 from:

Inks A and B may be prepared having the formulation described below in which the balance to 100 parts in each ink was made up with delonised water:

Component	Ink A	ink B
alkyl diol	12	15
2-pyrrelidone	5	2
polyethylene glycol	3.3	3.3
octyl dimethyl glycine	3.4	3.4
sodium hexadecyl ipherlyloxide disulfonate	0.5	0.5
oleyl triethoxy monodiphosphate	0.4	0.4
chelating agent	0.1	0.1
secondary ethoxylate	0.7	0.7
dicarboxylle acid	5	5
Dye from Example 1	3 ·	2.6
Deionised water	To 100 parts	To 190 parts



Further inks described in Tables I and II may be prepared wherein the Dye described in the first column is the compound from Example 1. Numbers quoted in the second column onwards refer to the number of parts of the relevant Ingredient and all parts are by weight. The links may be charged into an empty link jet printer cartridge (e.g. a HP 51625A or 51641A cartridge) and applied to paper by thermal or plezo link jet printing (e.g. Lising a HP - Deskilet 340, 540, 600, 840C, 930C or 932c thermal link jet printer).

The following abbreviations are used in Table I and II: PG = propylene glycol DEG = diethylene glycol 10 NMP = N-methyl pyrollidone DMK = dimethylketone IPA = Isopropanol MEOH = methanol-2P = 2-pyrollidone 15 MIBK = methylisobutyl ketone P12 = propane-1,2-dioi BDL = butane-2,3-diol CET= Tris(2-aminoethyl)amine buffer PHO = Na₂HPO₄ and 20 TBT = tertiary butanol

TDG = thiodiglycol

20 20 ASIMO 661458

圆
H

Dye	Water	.PG.	BEG	NMP	NMP DMK NaOH	ľ	. Na	.IPA	IPA. MEOH 2P.	•	MIBK
Content							Stearate				
20	80	rs.			4					ι.γ.	
3.0	.90		S.	rD.		0.2				······································	
10.0	82	er)		<u>(c.</u>	ო	48.4=			വ		
2.1	94		80								<u>-</u>
3.1	88	rc.					0.2	4			ເລ
1:1	<u>8</u>			63		0.5	0.5	1		හ	
2.5	90	4	15	ಣ	ಣ			\$	2	ഗ	4
വ	65		20					5			<u></u> :
2.4	75	z,	খ		ي				to		ಬ
4.1	80	m	£	8	9		0.3				
3.2	65		വ	4	Φ.			ري دي	4	9	ល
5.1	98								4		
10.8	06	нò					, , , , , , , , , , , , , , , , , , ,	ن			
10.0	8	7	9	2	වා			<u>, -</u>		4	
1.8	8		נט							<u>र</u>	,.
2.6	48			=						rts.	· · · ·
3.3	80	લ			10				લ		9
12.0	:80	:-	·		ru	6.3	•	جن.			
5.4	99	8	82	2	<u>_</u>		•			ಣ	ო
0	5	•		4		•		Ţ		5	

TABLE

								1991	PHO . PHO.		शुक्	·
	Water	PG	DEG.	DEG NMP CET	•	181	2		2	i		
Content										ß		
3.0	80	35			70			·	C.		เก	
9.0	. 06		ເລ		1	Ç	ć					
1.5	8	ນ	ໝ		0.15	0.0	y		0.12	4		
2.5	80		ဖ	4	(9	
3.1	82	4	8		E. 3			LC.	0.2			
6.0	82		5				5	>			···	
8.0	8	;	ໝ	<u>ت</u>			3			4	1	
4.0	92		10	4				- 0		<u> </u>		
2.2	75	4	9	(2)				4		3	<u>.</u>	
10.0	<u>8</u>			9		ç			0.95	r.		
0.6	92	_ ~-	Ç3.	_		0.0 -				ဖ		
5.0	78	ю	Έ							Į	•	
5.4	36					ç	,	ıc.	0.1	ເດ		
2.1	2	2	ហ	വ	5	7	5					
2.0	90		5				- 5					
8	88						ž Č			ຜ		
2	78		·	ın						rtj	•	
හ	.70	77		PQ			2 ~			72		
5	80)					\neg
1 20	80		9									



10

20

25

Claims

1. An lnk comprising a liquid medium and a tris-azo compound of Formula (1) or sailt thereof:

Formula (1)

wherein the liquid medium comprises water and an organic solvent.

An ink according to claim 1 which comprises:

(a) from 0.01 to 30 parts of a compound of Formula (1) or salt thereof, and

(b) from 70 to 99.99 parts of a liquid medium comprising water and an organic solvent;

wherein all parts are by weight and the number of parts of (a)+(b)=100.

- 3. An ink according to claim 2 wherein the number of parts of component (a) is from 1 to 5 parts and the number of parts of component (b) is from 99 to 95 parts.
 - 4. An Ink according to claim 2 or 3 wherein component (a) is completely dissolved in component (b).
 - An ink according to any one of the preceding claims wherein the liquid medium comprises one or more anionic and/or nonionic surfactants.
 - An ink according to any one of the preceding claims wherein the liquid medium comprises one or more pH buffers.
 - An ink according to any one of the preceding claims wherein the liquid medium comprises one or more blockes.
- 8. An ink according to any one of the preceding claims wherein the liquid medium comprises one or more metal chelators.
 - 9. An ink according to any one of the preceding claims having a pH of 3 to 6.
- 35 10. An link according to any one of the preceding claims having a viscosity at 25°C of less than 50cp

GB0304938

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

BLACK BORDERS

IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

FADED TEXT OR DRAWING

BLURRED OR ILLEGIBLE TEXT OR DRAWING

SKEWED/SLANTED IMAGES

COLOR OR BLACK AND WHITE PHOTOGRAPHS

GRAY SCALE DOCUMENTS

LINES OR MARKS ON ORIGINAL DOCUMENT

REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.